

POLYPROPYLENE

PPC 5660

Technical data sheet

Polypropylene - Heterophasic copolymer

DESCRIPTION >>

Polypropylene PPC 5660 is heterophasic copolymer with a Melt Flow Index of 7 g/10min.

Polypropylene PPC 5660 is characterised by a medium fluidity offering a combination of ease of processing and good manufactured article properties in applications ranging from household to industrial.

Polypropylene PPC 5660 has been developed for the manufacture of garden furniture, battery cases and other articles requiring a combination of good stiffness and impact properties

RHEOLOGICAL PROPERTIES >>

Property	Method	Unit	Value
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	7

MECHANICAL PROPERTIES >>

Property	Method	Unit	Value
Tensile Strength at Yield	ISO 527-2	MPa	25
Elongation at Yield	ISO 527-2	%	6
Tensile modulus	ISO 527-2	MPa	1300
Flexural modulus	ISO 178	MPa	1200
Izod Impact Strength (notched)	ISO 180	kJ/m ²	
at 23°C			10
at - 20°C			5.5
Charpy Impact Strength (notched)	ISO 179	kJ/m ²	
at 23°C			13
at - 20°C			6
Hardness Rockwell - R-scale	ISO 2039-2		85

THERMAL PROPERTIES >>



Property	Method	Unit	Value
Melting Point	ISO 3146	Å°C	165
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			65
10N-50°C per hour			135
Heat Deflection Temperature	ISO 75-2	°C	
1.80 MPa - 120°C per hour			50
0.45 MPa - 120°C per hour			92

OTHER PHYSICAL PROPERTIES >>

Property	Method	Unit	Value
Density	ISO 1183	g/cm ³	0.905
Bulk Density	ISO 1183	g/cm ³	0.525

DISCLAIMER

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TOTAL PETROCHEMICALS do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.



TOTAL PETROCHEMICALS RESEARCH FELUY
European Polypropylene Technical Services
Zone Industrielle C
B-7181 Feluy
Belgium

Technical data sheet - PPC 5660 • Page 3

Last updated: 11/10/2004
Contact: Martine Sebille
Fax: + 32 (0) 64 51 46 50
Email: felr-pp-ts-d@total.com
Web: www.polypropylene.totalpetrochemicals.biz