



LNP* Stat-kon* Compound M1HI

Europe-Africa-Middle East: COMMERCIAL

LNP* Stat-kon* M1HI is a compound based on Polypropylene resin. Added features of this material include: Electrically Conductive, High Impact.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yield, 5 mm/min	27	MPa	ISO 527
Tensile Stress, break, 5 mm/min	16	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4.3	%	ISO 527
Tensile Strain, break, 5 mm/min	24	%	ISO 527
Flexural Stress, break, 2 mm/min	40	MPa	ISO 178
Flexural Modulus, 2 mm/min	1600	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	60	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	1.3E-04	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.48E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	110	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	61	°C	ISO 75/Af
PHYSICAL			
Density	0.03	lb/in ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+04	Ohm	ASTM D 257

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
 3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
 4) Own measurement according to UL.

Source, GMD, Last Update: 01/02/2007

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA. All information, recommendation or advice given by General Electric Company USA, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of General Electric Company, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. General Electric Company, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of General Electric Company or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

* LNP is a trademark of the General Electric Company

* Stat-kon is a trademark of the General Electric Company

© 1997-2007 General Electric Company. All rights reserved



GE
Plastics

LNP* Stat-kon* Compound M1HI Europe-Africa-Middle East: COMMERCIAL

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
4) Own measurement according to UL.

Source, GMD, Last Update: 01/02/2007

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA All information, recommendation or advice given by General Electric Company USA, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of General Electric Company, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. General Electric Company, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of General Electric Company or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection

* LNP is a trademark of the General Electric Company

* Stat-kon is a trademark of the General Electric Company

© 1997-2007 General Electric Company. All rights reserved