

## RITFLEX® 647 | TEEE | Unfilled

### Description

Riteflex 647 is a thermoplastic polyester elastomer with nominal hardness of 47 Shore D and medium modulus.

Physical properties	Value	Unit	Test Standard
Density	<b>1170</b>	kg/m <sup>3</sup>	ISO 1183
Melt flow rate (MFR)	<b>8.5</b>	g/10 min	ISO 1133
MFR test temperature	<b>220</b>	°C	ISO 1133
MFR test load	<b>2.16</b>	kg	ISO 1133
Mold shrinkage - parallel	<b>1.3-1.8</b>	%	ISO 294-4
Mold shrinkage - normal	<b>1.5-1.9</b>	%	ISO 294-4
Water absorption (23°C-sat)	<b>0.5</b>	%	ISO 62


Mechanical properties	Value	Unit	Test Standard
Tensile modulus (1mm/min)	<b>125</b>	MPa	ISO 527-2/1A
Tensile stress at 50% strain (50mm/min)	<b>12</b>	MPa	ISO 527-2/1A
Tensile strain at break (50mm/min)	<b>300</b>	%	ISO 527-2/1A
Flexural modulus (23°C)	<b>125</b>	MPa	ISO 178
Flexural stress @ 3.5% strain	<b>4</b>	MPa	ISO 178
Charpy impact strength @ 23°C	<b>NB</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength @ -30°C	<b>NB</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength @ 23°C	<b>NB</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength @ -30°C	<b>NB</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Shore hardness D scale 15 sec value	<b>47</b>	-	ISO 868
Ross flex	<b>&gt;1000000</b>	cycles	Internal

Thermal properties	Value	Unit	Test Standard
Melting temperature (10°C/min)	<b>187</b>	°C	ISO 11357-1,-2,-3
DTUL @ 0.45 MPa	<b>62</b>	°C	ISO 75-1/-2
Coeff.of linear therm. expansion (parallel)	<b>2</b>	E-4/°C	ISO 11359-2
Flammability at thickness h	<b>HB</b>	class	UL94
thickness tested (h)	<b>1.5</b>	mm	UL94

Electrical properties	Value	Unit	Test Standard
Relative permittivity - 1 MHz	<b>4.6</b>	-	IEC 60250
Dissipation factor - 1 MHz	<b>400</b>	E-4	IEC 60250
Volume resistivity	<b>4E12</b>	Ohm*m	IEC 60093
Electric strength	<b>13</b>	kV/mm	IEC 60243-1
Comparative tracking index CTI	<b>&gt;600</b>	-	IEC 60112

**RITEFLEX® 647 | TEEE | Unfilled**

**Typical injection moulding processing conditions**



**Maximum residual moisture content: 0.0500%**

**Processing Temperatures:**

	ϕ <sub>Cavity</sub>	ϕ <sub>Melt</sub>	ϕ <sub>Hot Runner</sub>	ϕ <sub>Die</sub>	ϕ <sub>4</sub>	ϕ <sub>3</sub>	ϕ <sub>2</sub>	ϕ <sub>1</sub>	ϕ <sub>Feeding</sub>	ϕ <sub>Hopper</sub>
min (°C)	20	190	190	190	185	185	185	185	185	20
max (°C)	55	215	215	215	215	210	210	200	200	50

**Processing Pressures:**

No info

**Injection speed: medium - fast**

**Screw speed:**

Screw diameter (mm)	16	25	40
Screw speed (rpm)	200	140	80

**Pre-drying conditions:**

To avoid hydrolytic degradation during processing, Riteflex resins have to be dried to a moisture level equal to or less than 0.05%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 225°F (107°C) for 4 hours.

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

**Drying time: 4 h**

**Drying temperature: 100 - 110 °C**

**Special information:**

No special information available.

**Injection Molding**

Rear Temperature	370-390(185-200)	deg F (deg C)
Center Temperature	390-410(200-210)	deg F (deg C)
Front Temperature	390-420(200-215)	deg F (deg C)

## RITFLEX® 647 | TEEE | Unfilled

Nozzle Temperature	390-420(200-215)	deg F (deg C)
Melt Temperature	390-420(200-215)	deg F (deg C)
Mold Temperature	75-125(20-55)	deg F (deg C)
Back Pressure	0-50	psi
Screw Speed	Medium	
Injection Speed	Fast	

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

## Contact Information

### Americas

Ticona  
 Product Information Service  
 8040 Dixie Highway  
 Florence, KY 41042  
 USA  
 Tel.: +1-800-833-4882  
 Tel.: +1-859-372-3244  
 email: [prodinfo@ticona.com](mailto:prodinfo@ticona.com)  
 Ticona on the web: [www.ticona.com](http://www.ticona.com)

### Customer Service

Tel.: +1-800-526-4960  
 Tel.: +1-859-372-3214  
 Fax: +1-859-372-3125

### Europe

Ticona GmbH  
 Information Service  
 Tel.: +49 (0) 180-5842662 (Germany)\*  
 +49 (0) 69-30516299 (Europe)  
 Fax: +49 (0) 180-2021202 (Germany & Europe)\*\*  
 email: [infoservice@ticona.de](mailto:infoservice@ticona.de)  
 Internet: [www.ticona.com](http://www.ticona.com)

\*starting 01.01.2007 0,14€/minute + local landline rates

\*\*0,06€/Call + local landline rates

## General Disclaimer

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values.

Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use.

To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication.

Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards.

We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed (+49 (0) 69 30516299 for Europe and +1 859-372-3244 for the Americas) for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

The products mentioned herein are not intended for use in medical or dental implants.

© Copyright 2007, Ticona, all rights reserved. (Pub. 28-Feb-2007)